

Sioen Coating nv
Dhr. Bram Wydooghe
Fabriekstraat 23
8850 ARDOOIE



Your notice of
20-06-2017

Your reference
BE99/4500307227

Date
22-06-2017

Analysis Report 17.03629.01

Required tests :

BS 5867-2 (2008)

Identification number	Information given by the client	Date of receipt
T1713391	B81xx	20-06-2017

Gina Créelle

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be
Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1713391 - B81xx

Determination of the flammability of textile fabrics for curtains and drapes

Date of ending the test 22-06-2017
 Standard used EN ISO 15025 (2002)
 Product standard BS 5867-2 (2008)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Flame application time (s) 15

	Length			Width		
	1	2	3	1	2	3
Flame or hole on edge	no	no	no	no	no	no
Flaming debris droplets	no	no	no	no	no	no

Type B performance requirements

No part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge.

There shall be no separation of any flaming debris droplets

Conclusion Flammability complies with the requirements of BS 5867-2:2008, type "B"